

## **SPECIFICATION:**

### **EPDM RECLAIM:**

#### **Chemical**

<b>Properties :</b>	Ash %	20 Max
	Carbon Black %	20 Min
	Acetone Extract %	35 Max
	RHC By Difference %	30 Min

#### **Physical**

<b>Properties :</b>	Specific Gravity gm/cc	1.1 - 1.16
	Tensile Strength kg/cm <sup>2</sup>	60 Min
	Elongation at Break %	350 Min.
	Mooney Viscosity ML ( 1+4 ) @ 100 <sup>o</sup> C.	25-50
	Hardness Shore A	50 - 60