

SPECIFICATION:

NATURAL RECLAIM:

Chemical

Properties :	Ash %	20 - 30
	Carbon Black %	11 - 25
	Acetone Extract %	9 -15
	Volatile Matter %	1 Max.
	RHC By Difference %	42 Min.

Physical

Properties :	Specific Gravity gm/cc	1.2 - 1.3
	Tensile Strength kg/cm ²	30 Min.
	Elongation at Break %	250 Min.
	Mooney Viscosity ML (1+4) @ 100 ^o C.	25 - 55
	Hardness Shore A	55 - 65