

## **SPECIFICATION:**

### **NATURAL RECLAIM:**

#### **Chemical**

<b>Properties :</b>	Ash %	20 - 30
	Carbon Black %	11 - 25
	Acetone Extract %	9 -15
	Volatile Matter %	1 Max.
	RHC By Difference %	42 Min.

#### **Physical**

<b>Properties :</b>	Specific Gravity gm/cc	1.2 - 1.3
	Tensile Strength kg/cm <sup>2</sup>	30 Min.
	Elongation at Break %	250 Min.
	Mooney Viscosity ML ( 1+4 ) @ 100 <sup>o</sup> C.	25 - 55
	Hardness Shore A	55 - 65